





Field of Application

Applying dehumidifying finishing coating on-site to the interior walls of buildings and insulating anti-crack coating to exterior walls.

How to apply

Dehumidifying Coating of Interior Walls

The approximately 2mm interior dehumidifying double layer micro-coating is made as follows:

- 1. Using a roller without water, apply an initial coat of Primer Ecobios LIB;
- 2. Install a 45g/m² glass veil anchored with 1 coat of Primer Ecobios LIB, applied using a roller without water;
- 3. Using a hand trowel, apply 1 coat of no less than 500g/m² of TIXOS (in addition to the plaster), mixed with 30% alabaster plaster;
- 4. Using a roller without water, apply a second coat of Primer Ecobios LIB;
- 5. Using a hand trowel, apply a second coat of no less than 500g/m² of TIXOS (in addition to the plaster), mixed with 30% quick-drying alabaster plaster;
- 6. Using a roller without water, apply a third coat of Primer Ecobios LIB;
- 7. Using a roller without water, apply 2 coats of Solaria Universal ES milk- and wine vinegar-based mineral paint.

Insulating Coating of Exterior Walls

The approximately 2mm **exterior insulating double layer** micro-coating is made by replacing the quick-drying alabaster plaster with quick-drying concrete and completing the micro-coating with 2 coats of EcobioSun silky and/or El.i.T. using a roller and/or spraying it on. Air out (7÷20 days) before spending time in the treated rooms.

Warning label pursuant to Regulation (EC) 1272/2008 (CLP).





H318: Causes serious eye damage.

H315: Causes skin irritation

P280: Wear protective gloves/clothing and eye/face protection. Use proper industrial hygiene.

Contains: Hydrated lime; CAS. 1305-62-0; EC 215-137-3; Portland Cement Clinker.

EUH208: contains reaction mass of: 5-chloro-2-methyl-2H-isothiazolin-3-one (3:1) 2-OCTYL-2H-ISOTHIAZOL-3-ONE.

May cause an allergic reaction.

VOC: Maximum VOC content 30 g/l; maximum value permitted by EU (Cat. A/BA) is 30 g/l (2010). **Dispose** of packaging as special hazardous waste. **Info:** H CAV Foggia (Italy) + 39 800183459 (24/ 24).



Lotto n.14/A - Zona industriale - 73033 Corsano (Le) www.leuc.it - labo@ecobios-solaria.it - Info: +39 0833.533080

Contents 10 Kg